

H20G-00

POLYPROPYLENE HOMOPOLYMER

Product Description

H20G-00 is designed for general purpose injection molding applications. Typical applications include consumer products, housewares, and rigid packaging. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.¹

Typical Properties²

| Property | English Units | SI Units | ASTM Method |
|---------------------------------------|---------------|-------------|-------------|
| Resin Properties | | | |
| Density | | 0.910 g/cc | D792 |
| Melt Flow Rate (230°C/2.16 kg) | | 20 g/10 min | D1238 |
| Injection Molded Specimen Test | | | |
| Tensile Strength @ Yield | 5,200 psi | 36 MPa | D638 |
| Elongation @ Yield | 9.0 % | 9.0 % | D638 |
| Flexural Modulus, 1% Secant Method | 210,000 psi | 1,450 MPa | D790A |
| HDT @ 66 psi (455 kPa) | 217 °F | 103 °C | D648 |

¹Consult the Regulatory Position Statement for specific use conditions and limitations.

²Typical property values will vary and are not to be used as specification limits.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, please refer to the Regulatory Position Statement (RPS) online at www.ineos-op.com, or call + 1-800-527-5419.

Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Safety Data Sheet (SDS) contains the available product health and safety information for this material and can be found at www.ineos-op.com. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

The Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS O&P is altered or modified, different shipping descriptions may apply and the SDS of the original material should not be used.

All information contained herein, whether technical or otherwise, is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranties, express or implied, are made with respect to the accuracy, reliability, or completeness of this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA will not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information will not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.