

# ELTEX® LGB263N2070

## **Product Technical Information**

High Density Polyethylene – Milk blow moulding resins

## Benefits & Features

**ELTEX® LGB263N2070** high density polyethylene is a white compound manufactured by INEOS O&P Europe. It contains 5% titanium dioxide and is intended for the production of ESL milk bottles and coextrusion of bottles for the packaging of UHT sterilized milk

The resin is specifically designed for 1-, 3- or 6- layer bottles.

It guarantees the preservation of the organoleptic properties of milk and has the following essential properties:

- High density, ensuring good rigidity of finished products
- A melt viscosity which ensures easy processing
- A very low odour level

Conditions	Test Methods	Values	Units
190°C/2.16kg	ISO 1133-1	0.7	g/10min
190°C and 100 s-1	INEOS Test Method	1200	Pa.s
23°C	ISO 1183-1	990	kg/m³
23°C, 50mm/min	ISO 527-2	30	MPa
23°C, 1 mm/min	ISO 527-2	1250	MPa
	ISO 179-1/1eA	8.5	$kJ/m^2$
40°C, 6 N/mm² 2% Arkopal N100	ISO 16770	10	h
DSC 2nd heating 10°C/min	ISO 11357-3	134.0	°C
	INEOS Test Method	Medium	-
	190°C/2.16kg 190°C and 100 s-1 23°C 23°C, 50mm/min 23°C, 1 mm/min 23°C 40°C, 6 N/mm² 2% Arkopal N100 DSC 2nd heating 10°C/min	190°C/2.16kg 190°C and 100 s-1 INEOS Test Method  23°C ISO 1183-1  23°C, 50mm/min 23°C, 1 mm/min ISO 527-2 ISO 179-1/1eA 40°C, 6 N/mm² 2% Arkopal N100  DSC 2nd heating 10°C/min ISO 11357-3	190°C/2.16kg       ISO 1133-1       0.7         190°C and 100 s-1       INEOS Test Method       1200         23°C       ISO 1183-1       990         23°C, 50mm/min       ISO 527-2       30         23°C, 1 mm/min       ISO 527-2       1250         23°C       ISO 179-1/1eA       8.5         40°C, 6 N/mm²       ISO 16770       10         DSC 2nd heating 10°C/min       ISO 11357-3       134.0         INEOS Test Method       Medium

## Data should not be used for specification work

September, 2020 Published by INEOS Olefins & Polymers Europe

<sup>(1)</sup> Compression-moulded discs, cooled at the rate of 15°C per minute

<sup>(2)</sup> Apparent dynamic viscosity of the material extruded at 190°C through a 1.0 mm diameter and 15 mm long die, at apparent shear rate 100 s<sup>-1</sup>



# ELTEX® LGB263N2070

# Compliance to Regulations

**ELTEX® LGB263N2070** meets EU and FDA regulations governing the approval of materials used in the manufacture of packaging which may come into contact with food products.

INEOS will be happy to supply customers with certificates of conformity to the various national legislations.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration.

It is advised to process the product within maximum one year after delivery.

#### **Regulatory Information**

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website <a href="www.ineos.com">www.ineos.com</a> where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

## Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website <a href="www.ineos.com">www.ineos.com</a>. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

### **Exclusion of Liability**

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

Published by INEOS Olefins & Polymers Europe