



# ELTEX<sup>®</sup> MED PH23T630

## Product Technical Information

Low Density Polyethylene for Healthcare applications

### Benefits & Features

**ELTEX<sup>®</sup> MED PH23T630** is a LD-polyethylene for injection moulding having excellent flow properties allowing short cycle time or easy filling of long flow-paths. The moulded article is characterized by low degree of built-in stress & good flexibility

**ELTEX<sup>®</sup> MED PH23T630** is produced according to good manufacturing practice and is additive-free.

### Applications

**ELTEX<sup>®</sup> MED PH23T630** is recommended for injection moulding of:

- Flexible lids
- Caps and closures
- Pharmaceutical & diagnostic packaging

**ELTEX<sup>®</sup> MED PH23T630** can be sterilized with Eto-treatment or with Gamma radiation up till 50 kGy

Properties	Conditions	Test Methods	Values	Units
<b>Physical</b>				
Density		ISO1183-1 & ISO 1872-1	923	kg/m <sup>3</sup>
Melt Flow Rate	190°C/2.16 kg	ISO 1133-1	22	g/10 min
<b>Mechanical</b>				
Tensile Strain at Break	50 mm/min	ISO 527-1,-2	130	%
Tensile Modulus	1 mm/min	ISO 527-1,-2	180	MPa
Tensile Impact Strength, notched		ISO 8256/A1	160	kJ/m <sup>2</sup>
Hardness Shore D*		ISO 868	49	-
<b>Thermal</b>				
Heat Deflection Temperature	0.45 MPa	ISO 75-2	49	°C
Vicat Softening Temperature	10 N	ISO306/A50	92	°C

**Data should not be used for specification work**

\* Values determined on injection moulded specimens acc. to ISO 1872-2

### Compliance to Regulations on Medical use

**ELTEX<sup>®</sup> MED PH23T630** complies with the European Pharmacopoeia – Monograph 3.1.4 and meets the requirements of the USP29, <88> guideline concerning the biological reactivity test in vivo (so-called USP Class VI)



# ELTEX<sup>®</sup> MED PH23T630

## Processing guidelines

Melt temperature	180-230°C
Injection speed	Highest possible
Hold pressure	Just high enough to avoid sink marks
Mould temperature	10-40°C
Shrinkage	1.5-2% depending on wall thickness and moulding parameters

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

---

### Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website [www.ineos.com](http://www.ineos.com) where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

### Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website [www.ineos.com](http://www.ineos.com). Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

### Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

January, 2018

Published by

**INEOS** Olefins & Polymers Europe