

# Recycl-IN rLL9930



## DATA SHEET

### Product Technical Information

Recycl-IN rLL9930 is a natural hybrid polyethylene containing 32% of post-consumer recyclate.

### Benefits & Features

Recycl-IN rLL9930 is a ready-to-use hybrid polyethylene compound containing 32% of post-consumer recyclate (PCR) and supplied in a pellet form. The product is made from selected PCR materials and virgin polymers. Recycl-IN rLL9930 contains over 80% of linear polyethylene.

This resin presents:

- / Good balance between stiffness and film strength
- / Good optical properties
- / Good processability

### Applications

Recycl-IN rLL9930 is a polyethylene grade especially developed for artificial grass yarn, including textured yarn

## Recycl-IN rLL9930



Properties	Conditions	Test Methods	Values	Units
<b>Physical</b>				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	3.0	g/10min
Density		ISO 1183-1 & ISO 17855-1	935	kg/m <sup>3</sup>
<b>Film(*)</b>				
Dart drop impact	Method A	ASTM D1709	50	g
Elmendorf tear strength	MD/TD	ISO 1184	30/ 40	g/25µm
Tensile stress @ break	MD/TD	ISO 1184	55	MPa
Elongation @ break	MD/TD	ISO 1184	600	%
1% Secant Modulus	MD/TD	ISO 1184	300	MPa
Haze		ASTM D1003	5	%
Gloss (45°)		ASTM D2457	80	%

Data should not be used for specification work

(\*) 20µm film, 150m/min line speed, 260°C melt temperature – MD = machine direction, TD = transverse direction

# Recycl-IN rLL9930



## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

## Processing Guidelines

Recycl-IN rLL9930 in lean blends can be processed on most standard extrusion equipment. Optimization of conditions may be necessary, depending on the exact blend used. The recommended melt temperature range is 200 - 240°C.

### REGULATORY INFORMATION

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website [www.ineos.com](http://www.ineos.com) where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical

### sectors. HEALTH AND SAFETY INFORMATION

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website [www.ineos.com](http://www.ineos.com). Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

### EXCLUSION OF LIABILITY

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.