

## Provisional Product Technical Information

ELTEX® PF0110AZ is an additive free metallocene polyethylene plastomer resin produced in Europe.

## Benefits & Features

ELTEX® PF0110AZ is a polyethylene copolymer containing hexene-1 as comonomer and produced with a metallocene catalyst. It offers the following properties:

- Extremely low sealing initiation temperature and excellent Hot Tack strength
- Unrivalled impact strength and puncture resistance
- Very high gloss and transparency
- Softness and flexibility
- Excellent blending compatibility with other polyolefin grades

## Applications

ELTEX® PF0110AZ has been developed for use in various technical applications where its low crystallinity delivers superior sealing performance, enhanced toughness, better softness or higher elasticity. For instance, ELTEX® PF0110AZ can be used as sealant material in cast film compositions or extrusion coated structures.

ELTEX® PF0110AZ can be used pure or as a blending partner with other polyolefins. In addition, ELTEX® PF0110AZ offers easy extrudability.

We recommend that you consult your INEOS technical representative for further advice on the use of ELTEX® PF0110AZ.

Properties	Conditions	Test Methods	Values	Units
<b>Rheological</b>				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	10	g/10min
<b>Physical</b>				
Density ISO 1872-1	23°C	ISO 1183-2	902	kg/m <sup>3</sup>
<b>Mechanical*</b>				
Tensile Modulus		ISO 527-2	135	MPa
Tensile Strength at Yield	23°C	ISO 527-1,-2	6	MPa
Tensile strain at Yield		ISO 527-2	22	%
Tensile strength at Break		ISO 527-2	No break	MPa
Tensile strain at Break		ISO 527-2	>600	%
Flexural Modulus	23°C	ISO 178	120	MPa
Izod Impact Strength, notched	-20°C	ISO 180/A	No break	kJ/m <sup>2</sup>

# ELTEX<sup>®</sup> PF0110AZ

## Optical\*

Haze	70 µm	ASTM D 1003	1	%
Gloss	45°	ASTM D 2457	92	%

## Thermal

Peaks melting temperature (DSC)	INEOS Test Method	87 – 110	°C
---------------------------------	-------------------	----------	----

**Data should not be used for specification work**

\* Measurements made on compression moulded plaques

## Processing guidelines

**ELTEX<sup>®</sup> PF0110AZ** should be processed on machinery purpose designed for LLDPE. Melt temperatures in the range 190 - 250°C can be used.

For extrusion coating it is recommended to avoid extrusion temperatures above 280°C, not to jeopardize the sealing properties.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

## Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website [www.ineos.com](http://www.ineos.com) where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

## Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website [www.ineos.com](http://www.ineos.com). Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

## Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

November 2025

Published by

**INEOS** Olefins & Polymers Europe