



BPD8063

Product Technical Information

BPD8063 is a low density polyethylene compound having low dielectric loss properties meeting the needs of many coaxial and control cable applications. It contains a non staining antioxidant.

Specification

BPD8063 meets the following material specification:

- ISO 1872/1-PE, KN, 23-D022
- ASTM D 1248: Type I, Class A, Category 3, Grade E4

Regulations and approvals

Cables insulated with BPD8063 meet many national and international specifications for radio frequency (R.F.) cables. Information concerning suitability to a given specification is available from INEOS Polyolefins.

Packaging

BPD8063 is sold in pellet form and is available in the following packages: 25 kg bags, 1.1 ton holbins or bulk tankers.

Processing Data

The good processing characteristics of BPD8063 allow a wide latitude of both equipment and process conditions. Normally the extruder barrel temperatures should be set to give a resulting melt temperature in the range of 200-250 °C depending on the type of application.

Properties	Test Method	Value ⁽¹⁾	Units
Physical			
Melt flow rate	ISO 1133 Cond. D	1.5	g/10min
Conventional density conditioning ISO 1872/1	ISO 1183 Method D	923	kg/m ³
Low temperature brittleness	ISO 974	-75	°C
Oxidative induction time @ 200°C/Aluminium pan	SPT 005 ⁽³⁾	20	min
Tensile strength @ break	IEC 811-1-1 ⁽²⁾	12	MPa
Elongation @ break	IEC 811-1-1 ⁽²⁾	500	%
ESCR 100% "Igepal" F ₂₀	IEC 811-4-1	>48	h



BPD8063

Properties	Test Method	Value ⁽¹⁾	Units
Electrical			
Dielectric constant @ 1 MHz	ASTM D 1531	2.28	-
Dielectric loss angle @ 1 MHz	ASTM D 1531	50	μrad
Dielectric strength, short time	ASTM D 149	22	kV/mm
DC Volume Resistivity @ 23°C	ASTM D 257	>10 ¹⁴	Ω m

- (1) Data should not be used for specification work
- (2) Measured on plaques prepared according to SPT 002
- (3) INEOS O&P Europe test method

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolylefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.