

Product Information Bulletin

Durasyn[®] 125

Durasyn 125 polyalphaolefin is a fully synthesized hydrogenated hydrocarbon base fluid produced from linear alphaolefin feed stocks. Its engineered physical and performance properties are designed to extend the service life and enhance the performance of fully formulated lubricants operating under continuous low, high or wide temperature range conditions.

Features and Benefits

- Inherently thermally stable** ⇒ Resistant to thermal break down under non-routine high temperature excursions.
- Inherently oxidation resistant** ⇒ Extended replacement or reapplication cycles
- Engineered inherent low volatility** ⇒ Minimal top-off and reduced contamination of system components exposed to vapors
- Engineered to be highly shear stable** ⇒ Maintains viscosity grade over extended service life intervals
- Designed-in broad range viscometrics** ⇒ Suitable for exposure to low or high start-up or operating temperatures, or operation over wide temperature ranges

Intended Applications

Durasyn 125 is engineered for use in a wide variety of applications where the physical and performance properties of fully synthesized PAOs could be beneficial including:

- Reciprocating engine oils
- Gas and steam turbine oils
- Hydraulic and circulating oils
- Automatic and continuously variable transmission fluids
- Transportation and industrial gear oils

Compatibility

Durasyn 125 has been engineered to be either a near or direct substitute for existing PAO base oils and premium quality mineral oils. Compatibility with metals, elastomers, coatings and sealants is similar to other fully synthesized PAO base oils. Solubility is also similar to other fully synthesized PAO base oils.

TYPICAL PROPERTIES

Property	Test Method ISO/ASTM or	Unit Value	Typical Range
Specific Gravity , 15.6°C (60°F), kg/l (LB/gal)	12185 / D4052	0.824	0.82 -0.83
Viscosity Index	2909 / D2270	143	140 min
Viscosity , mm ² /s (cSt), 100°C (212°F)	3104 / D445	5.1	4.9 - 5.3
Viscosity , cSt, mm ² /s (cSt), 40°C (104°F)	3104 / D445	24.7	23.5 - 25.5

Refer to the reverse page of this bulletin for important technical, liability and warranty information

DURASYN 125 TYPICAL PROPERTIES (Continued)

Property	Test Method ISO/ASTM or	Unit Value	Typical Range
Cold Cranking Simulator , mPa • s (cP), -25°C	-- / D5293	770	NA
-30°C		1390	NA
-35°C		2220	NA
Brookfield Viscosity , mPa • s (cP), -26°C	D2983	1135	<2000
HTHS Viscosity 150°C , mPa • s (cP),	D4741	1.66	<1.8
Pour Point , °C (°F)	3016 / D97	-45	-40 max
Flash Point , °C (°F)	2592 / D92	250 / 500	245 / 473 min
Neutralizing Number (TAN) , mg KOH/g	6618 / D974	<0.01	0.01 max
Noack Volatility , 250°C, 1hr,%wt. Evap.	CEC L 40-A-93	5.5	6.0 max
Bromine Number , g Br/100 g	--/ IP-129	0.20	0.4 max
Air Release 50°C , min	D 3427	<1min	NA
Surface Tension , mN/m	D 1331	27.7	NA
Color	2049 / D1500	<0.5	0.5 max
Refractive Index @ 20°C		1.4579	1.4579+/- 0.0008
% Transmission @ 440 nm		99	>98
Molecular Weight	GC	519	
Elastomer Compatibility	CEC L-39-T-96	ON REQUEST	NA
RE1			
RE2			
RE3			
RE4			
Oxidation Tests			
TFOUT TEST	D 4742	On request	
DSC Oxidation	CEC L-85 T 99	On request	
Oxidation test	IP 48	On request	
Oxidation Stability	IP 306	On request	

Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, INEOS makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item not supplied by INEOS. The "Properties" and "Applications" listed in this document are not specifications. They are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED.

The name INEOS is a trademark of INEOS Capital Limited.