

Durasyn[®] 180 I

Durasyn 180I high viscosity polyalphaolefin is a fully synthesized and hydrogenated hydrocarbon base fluid produced from C10 linear alphaolefin feed stocks. Its engineered physical and performance properties are designed to extend the service life and enhance the performance of fully formulated lubricants operating under continuous low, high, or wide temperature range conditions.

Features and Benefits

- Inherent thermal stability** ⇒ Resistant to thermal break down under high temperature conditions.
- Inherently resistant to oxidation** ⇒ Allows the formulation of extended drain lubricants
- Engineered to be highly shear stable** ⇒ Maintains viscosity grade over extended service life
- Designed-in broad range viscometrics** ⇒ Suitable for exposure to low or high start-up or operating temperatures, or operation over wide temperature ranges

Intended Applications

Durasyn 180I is engineered for use in a wide variety of applications where the physical and performance properties of fully synthesized PAOs can be beneficial including:

- Gear Oils
- Compressor oils
- Greases
- Industrial Oils

Compatibility

Durasyn 180I has been engineered to be either a near or direct substitute for existing PAO fluids and premium quality oils. Compatibility with metals, elastomers, coatings and sealants is similar to other fully synthesized PAO base fluids. Solubility is also similar to other fully synthesized PAO base oils.

TYPICAL PROPERTIES

Property	Test Method ISO/ASTM or	Unit Value	Typical Range
Specific Gravity , 15.6°C (60°F), kg/l (LB/gal)	12185 / D4052	0.850	0.840 – 0.860
Viscosity Index	2909 / D2270	207	185 min
Viscosity , mm ² /s (cSt), 100°C (212°F)	3104 / D445	134	125 – 145
Viscosity , cSt, mm ² /s (cSt), 40°C (104°F)	3104 / D445	1261	1200 - 1350
Water , ppm,	D3401	8	50 max

Product Datasheet

DURASYN 180 I TYPICAL PROPERTIES (Continued)

Property	Test Method ISO/ASTM or	Unit Value	Typical Range
Pour Point, °C (°F)	3016 / D97	-37	-20 max
Flash Point COC, °C (°F)	2592 / D92	290	270 min
Flash Point PMC, °C (°F)	2592 / D93	265	-
Noack Volatility, 250°C, 1hr,%wt. Evap.	CEC L-40-A-93	0.8	-
Neutralizing Number (TAN), mg KOH/g	6618 / D974	0.002	<0.1 max
Bromine Number, g Br/100 g	--/ IP-129	0.2	0.4 max
Appearance		Clear/Bright	Observation
Color	D1209	<0.5	50 max
% Transmission @ 440 nm		99	>98

Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, INEOS makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item not supplied by INEOS. The "Properties" and "Applications" listed in this document are not specifications. They are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED.

The name INEOS is a trademark of INEOS Capital Limited.