

A white plastic jug is tilted, pouring a thick, white liquid into a clear glass. The liquid is captured mid-pour, creating a smooth, continuous stream. The background is a soft, neutral tone.

**INEOS**

**Olefins & Polymers Europe**

Your partner in

**EXTRUSION  
COATING**

**Comprehensive  
grade range**

|  
**INEOS**

# Goods that make your life convenient

INEOS Olefins & Polymers Europe



## Extrusion Coating

### **Perfectly suited for liquid food packaging, photographic paper, flexible and commercial packaging**

The extrusion coating market is a specialized market demanding for specific technical requirements. We are committed to working with our customers in order to continuously improve the performance of our resins.

#### Solutions to customers

- / Homopolymer LDPE grades such as 19N430/19N430B demonstrate an excellent combination of properties including processability and adhesion up to line speeds of 650m/min
- / INEOS Olefins & Polymers Europe extended its product range with low to high Ethylene-Methacrylic-Acid (EMAA) copolymers for demanding applications and adhesion. These grades are supplied into our key markets
- / We recommend that Metallocene LLDPE such as ELTEX® PF 1315AZ be selected for applications which require excellent ESCR and/or improved mechanical or sealing properties
- / Our dedicated team of technical experts and a world-class laboratory extrusion coating line can support customers and maximise the performance of their machinery and technology with our grades

INEOS Olefins & Polymers Europe has grown its position within the extrusion coating market, with special focus into new innovative products. Our 4 LDPE autoclave production lines, allow us to guarantee a secure and reliable supply from Europe to our worldwide customer base.



# Low Density Polyethylene Homopolymers

LDPE is the most commonly used polymer in extrusion coating. Our broad LDPE product range for extrusion coating fulfils different requirements on processing and/or application.

You can choose between LDPE grades with excellent draw down ability (20N430) or with very low neck in (17L430). The wide range of LDPE grade densities offer different barrier and sealing properties and also influence the tendency for blocking.

<b>Product name</b>	<b>MFR</b> 190°C/2.16kg g/10min ISO 1133	<b>Density</b> kg/m <sup>3</sup>  ISO 1183 method D	<b>DSC melting temperature</b> °C  INEOS method
17L430	4.0	917	107
17L430B	4.0	918	107
23L430	4.5	924	112
23L430B	4.5	923	111
19N430	7.5	920	109
19N430B	7.5	920	109
PH19N630	7.5	920	109
20N430	8.5	920.5	109
18R430	15	918	107



## Ethylene-Methacrylic-Acid Copolymers

The Ethylene-Methacrylic-Acid Copolymer (EMAA) grade range from INEOS Olefins & Polymers Europe low to high MAA content, shows improved adhesion characteristics especially to aluminium foil or to metallized films. It can be used in mono- or co-extrusion at high line speeds or at low coating weights and has a similar processing window to LDPE.

Product name	MFR 190°C/2.16kg g/10min ISO 1133	MAA Content % INEOS method	DSC melting temperature °C INEOS method
M21N430	7.5	1.2	108
M24N430	7.5	3.7	105
M28N430	8.0	8.3	101

## Metallocene Linear Low Density Polyethylene

The C<sub>6</sub> m-LLDPE grade range for extrusion coating shows an outstanding ESCR performance and improved sealing and mechanical properties compared to LDPE.

Product name	MFR 190°C/2.16kg g/10min ISO 1133	Density kg/m <sup>3</sup> ISO 1183 method D	DSC melting temperature °C INEOS method
ELTEX® PF1315AZ	15	914	96/114
ELTEX® PF1320AZ	20	913	96/114

## Polypropylene

PP has high temperature and grease resistance properties and therefore it is commonly used in the pet food market or for microwave oven applications. Here we are offering a ready to use modified PP (Eltex<sup>®</sup> P HEY500) for mono- or co-extrusion and a homopolymer PP grade (100-GA35) which can be used in co-extrusion or in blends with LDPE

Product name	MFR	Density	DSC melting temperature °C
	230°C/2.16kg g/10min ISO 1133	kg/m <sup>3</sup>  ISO 1183 method D	INEOS method
ELTEX <sup>®</sup> P HEY500	25	910	111/161
100-GA35	35	-	161

## High Density Polyethylene

Our HPDE grade with a very low gel level provides increased stiffness, higher gloss and lower tendency to blocking compared to LDPE. It can be used in blends for extrusion coating if a better WVTR, a higher temperature resistance and/or a better oil and grease resistance, is required.

Product name	MFR	Density	DSC melting temperature °C
	190°C/2.16kg g/10min ISO 1133	kg/m <sup>3</sup>  ISO 1183 method D	INEOS method
HD6070FA	7.6	960	132



## About us

INEOS is one of the world's largest chemical companies, founded in 1998. INEOS Olefins & Polymers Europe is a leading producer of olefins and polyolefins.

**INEOS Olefins & Polymers Europe** offers a full range of high value polyolefins solutions for market applications such as food and industrial packaging, pipe and automotive through dedicated sales, and technical service teams.

INEOS is a safe and environmentally responsible company. We are engaged in developing our sustainable agenda to improve our operations and to implement sustainable solutions for our customers. This includes products that offer lightweighting, energy efficiency, durability (extended lifetime) or conservation of resources. We care.



EXCLUSION OF LIABILITY: The information contained in this brochure, as at the date of publication, is accurate to the best knowledge and belief of INEOS Europe AG and its affiliates («INEOS») and any further information or advice provided by INEOS relating to INEOS or third party materials is also given in good faith. INEOS makes no representations or warranties, express or implied, regarding the completeness, quality or accuracy of this or any other information and any decisions you make based on the information contained in this brochure or otherwise provided by INEOS, including as to the suitability or fitness of materials for a particular purpose, are your sole responsibility. The information contained here is subject to change, and your INEOS representative will be happy to help in providing you with the latest version of this information. Please otherwise note that we advise you regularly check the validity of the information you may have already downloaded from our website. Except as required by mandatory law or as expressly provided in INEOS's standard terms and conditions of sale, INEOS accepts no liability whatsoever arising from the use of information supplied by this brochure or otherwise, or from the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS materials or the use of INEOS materials in conjunction with such other materials. Rigidex®, Eltex®, Eltex P®, Eltex PF®, Rigidex P®, Innovene, INEOS and the breakthrough mark are all trademarks of the INEOS group, used with its permission, and are registered in a number of countries.





Please visit our website at [www.ineos.com](http://www.ineos.com)  
or contact us at [ineospofcsc@ineos.com](mailto:ineospofcsc@ineos.com)

© INEOS Olefins & Polymers Europe, April 2020