

DURASYN® HIGH VISCOSITY POLYALPHAOLEFIN (PAO) TYPICAL PROPERTIES¹

Durasyn® PAO	174I	176	180R	180I
Color (ASTM D1500)	<0.5	<0.5	<0.5	<0.5
K. Viscosity, cSt, 100°C	50	63	102	134
K. Viscosity, cSt, 40°C	412	545	938	1,254
Viscosity Index	186	189	204	216
Pour Point, °C	<-35	<-35	<-20	<-20
Flash Point, °C	>265	>265	>265	>265
Specific Gravity (60/60°F)	0.846	0.850	0.856	0.856
Total Acid Number	<0.01	<0.01	<0.01	<0.01
Bromine Number	<1.0	<0.4	<0.4	<0.4

¹ The physical properties of INEOS polyalphaolefin materials are summarized in the table above. The values quoted were obtained from samples of production materials and are provided for guidance only. These are not intended to be specification properties.

Proprietary property of INEOS Oligomers.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, INEOS makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation for any use that may infringe patent rights or an endorsement of any particular material not supplied by INEOS. Any properties or applications listed in this bulletin are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty.