



BPD3801

Product Technical Information

BPD3801 is a polyethylene copolymer containing hexene-1 as the comonomer produced with a metallocene catalyst. **BPD3801** represents an interesting balance of properties for Wire & Cable applications.

When compounded with suitable additives, is designed for use in silane crosslinking processes (Monosil[®]). It has been developed for LV insulation or jacketing applications.

Benefits and Features

- Suitable Melt Index and Density for Wire & Cable applications
- High X-link efficiency
- Higher output and productivity
- High flexibility
- Very good Mechanical Properties and Stress Cracking Resistance
- Very good smoothness

Packaging

BPD3801 is sold in pellet form and is available in the following packages: 25 kg bags, 1.1 ton holbins or bulk tankers.

Processing Data

BPD3801 is a LLDPE base resin. A suitable antioxidant package should therefore be added to the product in order to meet heat ageing requirements.

The adoption of correct extrusion conditions and silane addition levels are of paramount importance for BPD3801.

Since LLDPE compounds exhibit different extrusion performance from conventional materials, modifying some extrusion parameters may be necessary to achieve optimum throughput rates.

BPD3801 can be run on existing Monosil equipment.

Correctly extruded insulations have a smooth surface with minimal gel defects. BPD3801 must be extruded in conjunction with 1.0 – 1.2 % of vinyl trimethoxysilane, a suitable peroxide and a crosslinking catalyst. Commercial mixtures can be used for this purpose.

Typical melt temperature to give satisfactory extrudates will be in the region of 225-235 °C

On a commercial line 150mm - 30 L/D a typical temperature profile would be:

Barrel: 150-160-170-180-190-200-210°C Head: 210-220-230°C Die: 270°C

Screw cooling: 80°C



BPD3801

Properties:

Properties		Test Method	Value	Units
Physical				
Melt flow rate	2.16 kg load	ISO 1133-1	5.5	g/10min
Conventional density		ISO 1872-1	916	kg/m ³
Electrical				
Volume Resistivity		ASTM D 257	>10 ¹⁶	ohm.cm
Dielectric constant	@ 50 Hz	ASTM D 150-2.2	2.3	
Dissipation factor	@ 50 Hz	ASTM D 150	< 0.004	-

* Data should not be used for specification work

Physical properties of grafted BPD3801

BPD3801 when grafted in the laboratory with 1.1 % of a suitable silane/peroxide mixture and 0.05 % of a tin condensation catalyst, typically gives the following results on a 1.5 mm² cable after curing 4h in water at 80 °C.

Properties		Test Method	Value	Units
Tensile strength	@ break	IEC 811-1-1	20	MPa
Elongation	@ break	IEC 811-1-1	>300	%
Hot set test		IEC 811-2-1	60	%

* Data should not be used for specification work



BPD3801

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.