

# **Product Datasheet**

# Durasyn® 156

**Durasyn 156 polyalphaolefin** is a fully synthesized distilled and hydrogenated hydrocarbon base fluid produced from C1214 linear alphaolefin feed stocks. Its engineered physical and performance properties are designed to extend the service life and enhance the performance of fully formulated lubricants operating under continuous low, high or wide temperature range conditions.

#### **Features and Benefits**

Inherently thermally stable

Inherently oxidation resistant
Engineered inherent low volatility

Engineered to be highly shear stabile 

⇒ Designed-in broad range viscometrics 

⇒

- ⇒ Resistant to thermal break down under non-routine high temperature excursions.
- ⇒ Extended replacement or reapplication cycles

- Suitable for exposure to low or high start-up or operating temperatures, or operation over wide temperature ranges

## Intended Applications

Durasyn 156 is engineered for use in a wide variety of applications where the physical and performance properties of fully synthesized PAOs could be beneficial including:

- Reciprocating engine oils
- Gas and steam turbine oils
- Hydraulic and circulating oils
- Transportation and Industrial Oils

## Compatibility

Durasyn 156 has been engineered to be either near or direct substitutes for existing PAO base oils and premium quality mineral oils. Compatibility with metals, elastomers, coatings and sealants is similar to other fully synthesized PAO base oils. Solubility is also similar to other fully synthesized PAO base oils.

### TYPICAL PROPERTIES

Property	Test Method ISO/ASTM or	Unit Value	Unit Range
Specific Gravity, 15.6°C (60°F), kg/l (LB/gal)	12185 / D4052	0.828	0.810 - 0.840
Viscosity Index	2909 / D2270	145	140 min
Viscosity, mm2/s (cSt), 100°C (212°F)	3104 / D445	6.1	5.8 – 6.3
Viscosity, cSt, mm2/s (cSt), 40°C (104°F)	3104 / D445	32.0	28.0 - 34.0

# **Product Datasheet**

# **TYPICAL PROPERTIES** (Continued)

Property	Test Method ISO/ASTM or	Unit Value	Unit Range
Cold Cranking Simulator, mPa • s (cP),	/ D5293		
-30°C -35°C		2,300 3,880	N/D N/D
Pour Point, °C (°F)	3016 / D97	-36	-33 max
Flash Point, °C (°F)	2592 / D92	250/500	245 – 473
Noack Volatility, 250°C, 1hr,%wt. Evap.	CEC L-40-A-93	7.0	9.0 max
Neutralizing Number (TAN), mg KOH/g	6618 / D974	0.005	<0.01 max
Air Release,min.		< 1	<1
Bromine Number, g Br/100 g	/ IP-129	0.20	0.4 max
Aniline Point, °C		133.4	-
Appearance		Clear/Bright	Observation
Color	2049 / D1500	<0.5	0.5 max
Refractive Index @ 20°C		1.4593	1.4593 +/- 0.0008
% Transmission @ 440 nm		99	>98

#### **EXCLUSION OF LIABILITY**

INEOS Oligomers is a trading name for INEOS Europe Limited.

Except as required by mandatory law, INEOS accepts no liability whatsoever arising out of the use of information supplied herein, the use of other materials in lieu of INEOS materials or the use of INEOS materials in conjunction with such other materials.

Information contained in this publication is accurate to the best of the knowledge and belief of INEOS Europe Ltd and its affiliates ("INEOS"). However, INEOS makes no representations or warranties express or implied, regarding the completeness, quality or accuracy of this information and any decisions you make based on the information contained herein are your sole responsibility.

responsibility.

Any information or advice obtained from INEOS otherwise than by means of this publication and whether relating to INEOS materials or other materials, is also given in good faith. However, it remains at all times the responsibility of the customer to ensure that INEOS materials are suitable for the particular purpose intended.

Insofar as materials not manufactured or supplied by INEOS are used in conjunction with or instead of INEOS materials, the customer should arrange to obtain from the manufacturer or supplier all technical data and other information relating to such materials.