# 20T930

## **Product Technical Information**

LDPE for Injection moulding and compounding.

### Benefits & Features

20T930 is a low-density polyethylene intended for injection moulding or for the production of compounds and master-batches. It is a high MFR material, having good flow properties and allowing short cycle time and good additives and pigments dispersion. The moulded article is characterised by low degree of built-in stress, good stiffness and high gloss.

## **Applications**

20T930 is recommended for injection moulding of flexible products which require good flow properties and short cycle time. The material is especially suitable for thin walled products like caps and closures, household goods and toys.

It is also recommended for the manufacturing of highly filled compounds.

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190°C/2.16kg	ISO 1133-1	20	g/10min
Physical				
Density ISO 17855-1	23°C	ISO 1183-1	920	$kg/m^3$
Mechanical				
Tensile strain at Break Tensile Impact Strength, notched Tensile Modulus Shore Hardness	23°C, 50 mm/min 23°C, 1 mm/min Shore D	ISO 527-2 ISO 8256 ISO 527-2 ISO 868	120 160 170 39	% kJ/m² MPa
Thermal				
Vicat Softening Temperature	10N	ISO306/A50	77	°C
Data should not be used for specification work				

## Processing guidelines

For Injection Moulding:

20T930 can be injected over the usual melt temperature range 190 - 250°C depending on part thickness, with high injection speeds in a cold mould regulated with water cooled usually at 14°C between 10 to 20°C.

July, 2017 Published by INEOS Olefins & Polymers Europe

## 20T930

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration.

It is advised to process the product within maximum one year after delivery.

### **Regulatory Information**

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website <a href="www.ineos.com">www.ineos.com</a> where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

### Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website <a href="www.ineos.com">www.ineos.com</a>. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

### **Exclusion of Liability**

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

Published by INEOS Olefins & Polymers Europe